

PRODUCTS FOR THIS PROJECT

Tekta Crystal Clear sheet (001401-0380-F)
 Fiber Paper (7036)
 Bullseye GlasTac (8234) (8232)
 Ball Surface Mold (8733)
 Spartan Glass Cleaner Concentrate (8236)
 Disposable Particulate Respirator N95 (8260)
 Disposable Particulate Respirator N100 (8261)
 Bullseye Shelf Primer (8220) (8222)

FIRING SCHEDULES FOR THIS PROJECT
Full Fuse Firing

	RATE	TEMPERATURE	HOLD
1	300° F (167° C)	1225° F (663° C)	:05
2	600° F (333° C)	1520° F (827° C)	:30
3	AFAP	900° F (482° C)	2:00
4	100° F (56° C)	800° F (427° C)	:00
5	180° F (100° C)	700° F (371° C)	:00
6	600° F (333° C)	70° F (21° C)	:00

Slump Firing

	RATE	TEMPERATURE	HOLD
1	200° F (111° C)	1180° F (663° C)	1:00
2	AFAP	900° F (482° C)	2:00
3	100° F (56° C)	800° F (427° C)	:00
4	180° F (100° C)	700° F (371° C)	:00
5	600° F (333° C)	70° F (21° C)	:00